



Performance Paint Systems

CCM Fence Finish - Data Sheet

Description:

CCM Fence Finish is an economical, easy to apply, solid colour Fence Finish, able to be applied to all types of timber fences. Available in four high coverage, popular colours that are durable and easily maintained. Usually one coat will cover but two are recommended for evenness of colour and finish.

Physical Properties:

Resin type:	Acrylic emulsion
Solvent:	Water
Colour:	Redwood, Charcoal, Brown, Karaka.
Finish:	Low sheen to Matt
Drying Time:	Touch; 30 minutes, Overcoat in 2 hours
Theoretical Coverage:	Approximately 8 M ² /lt. depending on porosity.
Dry film thickness:	30 microns at 12 M ² /lt.
Thinning and cleanup:	Water

Application:

CCM Fence Finish may be applied by Brush, Roller or spray. Do not thin more than 5% with water. Stir thoroughly with flat stick until contents are evenly mixed before use, and occasionally when using to keep pigments evenly distributed.

Limitations:

Do not apply when temperature is below or expected to fall under 10°C or if rain is forecast within 24 hours of application.

CCM Fence Finish is a cost effective finish, it has no warranty, but will give a perfect low sheen finish on new planed or rough sawn timber fencing.

Substrate Preparation:

Ensure all surfaces are clean and dust free. If mould and fungus is present, treat with CCM House Wash. Water blasting is the recommended method of surface preparation.

For low gloss level precoated fences no preparation is required. For high gloss level fences sanding to a matt finish is the recommended method of preparation.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof. In no event will Commercial Coating Manufacturers Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.